

As diverse as your requirements

- ✓ Different materials for different requirements
- ✓ Various variants have marine edges for collecting spilt liquids
- ✓ Rectangular and octagonal shapes
- ✓ Harmoniously coordinated colours



Colours, shapes and edge finishes

✓ Colour


- Baltic Blue (NCS S 2030 R70B)
- White (similar to RAL 9010)
- Grey (similar to RAL 7035)
- Stainless steel
- Other colours upon request


✓ Shapes

- Rectangular worktops
- Outside corner worktops, octagonal
- Inside corner worktops, octagonal

✓ Edge finishes

- With marine edges
- Without marine edges





	Standard worktop depths
Rectangular*	400**, 600, 750, 900
Octagonal 90°	750 900
Octagonal 180°	750 750 900 900
Octagonal 360°	1500 1800

Width: running metres

Depths in front of a service wall: 670 mm and 820 mm

**Without marine edge only

Dimensions [mm]




Standard melamine



TopResist melamine



HPL / TRESPA TopLab® BASE




HPL / TRESPA TopLab® PLUS /
Fundermax Max Resistance²



Solid ceramic



Composite ceramic



Composite glass



Polypropylene



Epoxy



Stainless steel

Worktop resistance to solvents

Solvents	Standard melamine	TopResist® melamine	Trespa® Toplab® ^{BASE}	Trespa® Toplab® ^{PLUS} / Fundermax Max Resistance ²	Ceramic / Composite ceramic	Composite glass	Stainless steel	Epoxy resin	Polypropylene
Ethanol	+	+	+	+	+	+	+	+	+
Isopropanol	+	+	+	+	+	+	+	+	+
Acetone	+	+	+	+	+	+	+	+	+
Ethyl acetate	+	+	+	+	+	+	+	+	0
Trichloromethane	+	+	+	+	+	+	+	-	+
Diethyl ether	+	+	+	+	+	+	+	+	0
Toluene	+	+	+	+	+	+	+	+	-
n-Hexane	+	+	+	+	+	+	+	+	0
White spirit	+	+	+	+	+	+	+	+	0

+ Material is suitable, 0 Material is conditionally suitable, – Material is unsuitable

Worktop resistance to inorganic acids

Inorganic acids	Standard melamine	TopResist® melamine	Trespa® Toplab® ^{BASE}	Trespa® Toplab® ^{PLUS} / Fundermax Max Resistance ²	Ceramic / Composite ceramic	Composite glass	Stainless steel	Epoxy resin	Polypropylene
Hydrochloric acid, concentrated	–	+	–	+	+	+	–	+	0
Sulphuric acid, concentrated	–	–	–	+	+	+	–	–	–
Sulphuric acid, 50%	–	0	–	+	+	+	–	+	+
Nitric acid, concentrated	–	–	–	+	+	+	–	–	–
Phosphoric acid, concentrated	–	+	–	+	+	+	–	+	+
Hydrofluoric acid	–	–	–	–	–	–	–	–	+
Aqua regia	–	0	–	+	+	+	–	+	–

+ Material is suitable, 0 Material is conditionally suitable, – Material is unsuitable

Worktop resistance to organic acids and alkalis

Organic acids	Standard melamine	TopResist® melamine	Trespa® Toplab® ^{BASE}	Trespa® Toplab® ^{PLUS} / Fundermax Max Resistance ²	Ceramic / Composite ceramic	Composite glass	Stainless steel	Epoxy resin	Polypropylene
Formic acid, concentrated	–	+	–	+	+	+	–	+	+
Acetic acid, concentrated	–	+	–	+	+	+	–	+	+

Alkalis	Standard melamine	TopResist® melamine	Trespa® Toplab® ^{BASE}	Trespa® Toplab® ^{PLUS} / Fundermax Max Resistance ²	Ceramic / Composite ceramic	Composite glass	Stainless steel	Epoxy resin	Polypropylene
Sodium hydroxide, 20%	–	+	–	+	+	+	–	+	+
Ammonia solution, concentrated	–	+	–	+	+	+	–	+	+

+ Material is suitable, 0 Material is conditionally suitable, – Material is unsuitable

Worktop resistance to neutral solutions and oxidants

Neutral solutions	Standard melamine	TopResist® melamine	Trespa® Toplab® ^{BASE}	Trespa® Toplab® ^{PLUS} / Fundermax Max Resistance ²	Ceramic / Composite ceramic	Composite glass	Stainless steel	Epoxy resin	Polypropylene
Formaldehyde, 25%	+	+	+	+	+	+	+	+	+
Oxidants	Standard melamine	TopResist® melamine	Trespa® Toplab® ^{BASE}	Trespa® Toplab® ^{PLUS} / Fundermax Max Resistance ²	Ceramic / Composite ceramic	Composite glass	Stainless steel	Epoxy resin	Polypropylene
Hydrogen peroxide, 30%	-	+	-	+	+	+	+	+	-
Potassium permanganate, 5%	-	+	-	+	+	+	-	+	-
Potassium dichromate, 5%	-	+	-	+	+	+	-	+	-
Iodine 5% in chloroform	-	+	-	-	+	+	-	+	-

+ Material is suitable, 0 Material is conditionally suitable, – Material is unsuitable

Worktop resistance to reductants, dyes and stains

Reducants	Standard melamine	TopResist® melamine	Trespa® Toplab® ^{BASE}	Trespa® Toplab® ^{PLUS} / Fundermax Max Resistance ²	Ceramic / Composite ceramic	Composite glass	Stainless steel	Epoxy resin	Polypropylene
Sodium sulphite, 5%	+	+	+	+	+	+	+	+	+
Dyes and stains									
Dyes and stains	Standard melamine	TopResist® melamine	Trespa® Toplab® ^{BASE}	Trespa® Toplab® ^{PLUS} / Fundermax Max Resistance ²	Ceramic / Composite ceramic	Composite glass	Stainless steel	Epoxy resin	Polypropylene
Eosin	0	0	+	+	0	0	+	+	+
Methylene blue	0	0	+	+	0	0	+	+	+
Crystal violet	0	0	+	+	0	0	+	+	+

+ Material is suitable, 0 Material is conditionally suitable, – Material is unsuitable